

AMENDMENTS TO THE CLAIMS

The following listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

Claims 1-10 (Cancelled).

Claim 11 (Currently amended): A process for producing a flatted coating which comprises:

- (a) introducing into a self-curing or radiation-curing coating system ~~[[a]]~~ at least one liquid dimerdiol (meth)acrylate, ~~flattening agent~~ in an amount effective to flat the coating system, said dimerdiol (meth)acrylate ~~flattening agent~~ having a degree of esterification of at least 50%, to form a flatted coating system;
 - (b) applying a coating of the flatted coating system to a substrate comprising glass; and
 - (c) curing the coating,
- wherein ~~said~~ the cured coating is flatted with respect to the same coating without said at least one dimerdiol (meth)acrylate ~~flattening agent~~.

Claim 12 (Previously presented): The process of claim 11, wherein, from 1% to 25% by weight of the dimerdiol (meth)acrylate is added to the coating system based on the weight of the coating system.

Claim 13 (Previously presented): The process of claim 11, wherein, the dimerdiol (meth)acrylate has a degree of esterification of at least 80%.

Claim 14 (Currently amended): The process of claim 11, wherein, the ~~flattening agent~~ flatted coating system further comprises a solid flattening agent.

Claim 15 (Previously presented): The process of claim 12, wherein, the dimerdiol (meth)acrylate has a degree of esterification of at least 80%.

Claim 16 (Currently amended): The process of claim 12, wherein the ~~flatting agent~~ flatted coating system further comprises a solid flatting agent.

Claim 17-18 (Cancelled):

Claim 19 (Currently amended): A method for flatting a substrate surface comprising glass, comprising the steps of applying a self-curing and/or radiation-curing coating system to said a substrate surface comprising glass, and curing, wherein said self-curing and/or radiation-curing coating system comprises ~~[[a]]~~ at least one liquid dimerdiol (meth)acrylate ~~flatting agent~~ having a degree of esterification of at least 50%, in an amount effective to flat the cured coating, and wherein said cured coating is flatted with respect to the same coating without said at least one dimerdiol (meth)acrylate ~~flatting agent~~.

Claim 20-21 (Cancelled):